



New Day International Trade Co.,Zhejiang

URL:www.newdaytrading.com Email:tony@newdaytrading.com

MSN:newdaytrading@hotmail.com Yahoo ID:newdaytrading@yahoo.cn

ADD: Room 302, Unit 1, 72nd Building, Danxi No.2 Residential Quarter, YIWU, Zhejiang, P.R.C.

Tel:86 579 8158 9460 Fax: 86 579 8158 9460

MAGNETIC PROPERTIES of RUBBER MAGNET

Physical properties	Unit	Values
(Remanence)Br	Gs(Mt)	1,650
(Coercive)Hcb	Oe(KA/m)	1,300
(Max.energy)BH max.	MGOe(KJ/m ³)	≥0.6MGOe
Tensile strength	Kg/cm ²	≥45
Break Extend Rate	%	≥50%
Hardness	HS	94~98
Turnover	Angle	180
Flexibility	mm	≤ φ 20
Density	g/cm ³	3.8