

Injection Molded NdFeB Magnetic Compound Property:

N/P	Br (kG)	H _{CB} (kOe)	H _{CJ} (kOe)	(BH) max (MGOe)
YXNA3	3.60~4.10	2.7~3.3	8.00~9.10	2.80~3.40
YXNA4	4.10~4.60	3.2~3.9	8.30~9.30	3.80~4.40
YXNA5	4.60~5.10	3.8~4.3	8.50~9.40	4.80~5.40
YXNA6	5.10~5.70	4.2~4.6	8.80~9.50	5.80~6.40
YXNA7	5.40~5.70	4.5~4.9	9.00~9.70	6.50~7.10
YXNA8A	5.90~6.30	4.8~5.3	8.80~9.70	7.30~7.80
YXNA8B	6.10~6.50	4.8~5.3	9.10~9.70	8.20~8.70

If you would like to learn more about our products, please feel free to visit our website <http://www.x-magnet.net/Magnet-Compound/NdFeb-Compound.html> or inquire us at yingli@magnets.com.cn at any of your convenience.