

Physical & Magnetic properties Of Injection SmCo Bonded Magnet made by SmCo compound:

P/N	SCI-3	SCI-3M	SCI-8
Br(mT)	300~400	350~550	550~680
bHc(kA/m)	199~279	247~358	334~462
iHc(kA/m)	716~1194	716~1194	716~1194
(BH)max(kJ/m ³)	20~28	32~52	48~64

If you would like to learn more about our magnetic powder and compound, please feel free to visit our website www.x-magnet.net or inquire us at yingli@magnets.com.cn at any of your convenience.