

Material	Code	Remanence Br		Coercivity Force		Intrinsic Coercivity Force		Max. Energy Product Bhm		Curie Temperature °C	Max. Operating Temperature °C
		T	KGs	KA/m	KOe	KA/m	KOe	KJ/m <sup>3</sup>	MGOe		
Bonded											
SmCo(1:5)	YB-6	0.4	4.0	280	3.5	800	10	30-50	4-6	-	120
	YB-10	0.5	5.0	320	4.0	800	10	50-65	6-8	-	120
SmCo(2:17)	YBG-10	0.6	6.0	360	4.5	800	10	65-80	8-10	-	120
	YBG-12	0.7	7.0	400	5.0	800	10	80-95	10-12	-	120