

永磁铁氧体材料技术参数  
magnetic properties of hard ferrites

材料牌号	剩磁 Br mT	矫顽力 H <sub>CB</sub> kA/m	内禀矫顽力 H <sub>cJ</sub> kA/m	最大磁能积 (BH) max kJ/m <sup>3</sup>	对应国际标准 材料牌号
Y26H	360-390	245-255	250-265	26.5-28.0	HF22/30
Y27	360-370	265-295	330-370	26.0-28.0	HF24/35
Y28	390-400	240-255	245-265	27.0-30.0	HF26/26
Y30H-1	390-400	255-275	265-290	28.0-32.5	HF29/22
Y30H-2	395-415	275-300	310-335	28.5-32.0	HF31/30
Y33	410-430	240-260	245-270	31.5-35.0	HF32/17
Y34	400-420	255-275	265-285	30.5-34.5	HF32/25
Y35	430-450	235-250	240-255	33.1-38.2	HF35/25
Y36	430-450	250-275	260-290	35.1-38.3	HF38/27
Y38	440-460	290-320	300-335	36.6-40.6	HF36/34
Y40	440-460	330-360	340-380	37.6-41.8	HF33/38

