

KSHS Filter Paper Technical Parameters

Email: trade2@grindingchina.com sherry_turbo@hotmail.com Tel:+86-10-6572 9550 Mob: 86-13439735750 Skype: sherryturbo Wechat:13439735750

Item	Model	Thickness (mm)	Weight (g/m ²)	Material	Longitudinal Strength (N/5cm)	Transverse Strength (N/5cm)	Air Permeability (L/ m ² s)	Filter Precision (μm)
1	KSPT-30	0.17±0.05	30±5	Polyester	60	15	3400	45-55
2	KSPT-40	0.26±0.05	40±5	Polyester	100	19	3000	35-45
3	KSPT-50	0.28±0.05	50±5	Polyester	110	25	2300	25-35
4	KSPT-60	0.30±0.05	60±5	Polyester	125	35	1800	15-25
5	KSPT-90	0.50±0.05	90±5	Polyester	220	52	650	8-12
6	KSPET-40	0.25-0.28	40	Polyester	100	60	—	40-50
7	KSPET-60	0.28-0.3	60	Polyester	120	80	—	30-40
8	KSPET-90	0.4-0.42	90	Polyester	135	96	—	10-15
9	KS-T70	0.37-0.4	70	Polyester	190	65	—	18-22
10	KS-T90	0.43-0.46	90	Polyester	230	85	—	12-18
11	KS-T150	0.75-0.8	150	Polyester	360	140	—	5-10
12	KSPP-30	0.17-0.2	30	Polypropylene	90	50	—	50-60
13	KSPP-40	0.21-0.27	40±4	Polypropylene	70-90	30-50	1000-1500	30-40
14	KSPP-60	0.35-0.38	60	Polypropylene	190	105	—	15-25
15	KSPP-80	0.4-0.42	80	Polypropylene	210	130	—	10-15