

TEST REPORT

No. : SHIN2303003333ML02_EN

Date : 2023-03-15

Page: 1 of 2



CUSTOMER NAME: NINGBO LARGE STONES HARDWARE & ELECTRICAL TRADING CO;LTD.

ADDRESS: NO.D-58, TIANDESHANGDU,YUYAO,NINGBO,ZHEJIANG

Sample Name : 304 RAW MATERIAL FOR STAINLESS STEEL FASTENERS

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Test Required : Tensile Test
SGS Ref. No. : 16290502
Date of Receipt : 2023-03-09
Testing Start Date : 2023-03-09
Testing End Date : 2023-03-15
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd..

Ranger Wei
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 t(86-21) 61196300 f(86-21) 68183122/68183920 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编:201319 t(86-21) 61196300 f(86-21) 68183122/68183920 e sgs.china@sgs.com

TEST REPORT

No. : SHIN2303003333ML02_EN

Date : 2023-03-15


Page: 2 of 2

1. Tensile Test

Test Method:GB/T 228.1-2021

Test Rate Control: A224

Test item	Specimen type	Tensile strength (R_m) (MPa)	Proof strength ($R_{P0.2}$) (MPa)	Elongation after fracture(A) $L_o = 5d$ (%)
Result-002	Unmachined specimen	591	269	68.0



*****End of report*****

In the territory of the People's Republic of China, the test report with CMA logo expresses that the test items are within the scope of China Metrology Accreditation(CMA); without CMA logo expresses that part/all of the test items are not within the scope of China Metrology Accreditation(CMA), and just for client internal reference.

